

Datasheet: EN CuZn36Pb2As / CW602N Brass with Lead Profiles, Bars & Rods for general purposes Alumeco ApS 06-05-2025				Internal alloy name: CW602N Metal: Brass Chemical Symbol: CuZn36Pb2As EN: EN CuZn36Pb2As UNS: C35330 SIS: - GB: - JIS: C3533 Also known as: Dezincification resistant Alloy type: Brass with lead																																																																																																																																																				
Main usage: Faucets, fittings and pipes for industrial or homes Components with underground usage Machined parts, bolts, rivets and screws Components for water boiler, condenser and heat exchanger Main properties: Excellent machinability Dezincification resistant Good resistance to corrosion against water, steam and other organic fluids.				Important norms and literature: General Standards EN 12164:2016: Copper and copper alloys – Rod for free machining purposes Geometric Tolerance EN 12164:2016: Copper and copper alloys – Rod for free machining purposes EN 12165:2024: Copper and copper alloys – Wrought and unwrought forging stock EN 12167:2016: Copper and copper alloys – Profiles and bars for general purposes																																																																																																																																																				
Chemical composition in %: EN 12164:2024 <table><tr><td>Cu</td><td>Al</td><td>As</td><td>Fe</td><td>Ni</td><td>Pb</td><td>Sn</td><td>Zn</td><td>Others</td></tr><tr><td>61,0 – 63,0</td><td>Max. 0,05</td><td>0,02 – 0,15</td><td>Max. 0,1</td><td>Max. 0,3</td><td>1,7 – 2,8</td><td>Max. 0,1</td><td>Remaining</td><td>Max. 0,2</td></tr></table>								Cu	Al	As	Fe	Ni	Pb	Sn	Zn	Others	61,0 – 63,0	Max. 0,05	0,02 – 0,15	Max. 0,1	Max. 0,3	1,7 – 2,8	Max. 0,1	Remaining	Max. 0,2																																																																																																																															
Cu	Al	As	Fe	Ni	Pb	Sn	Zn	Others																																																																																																																																																
61,0 – 63,0	Max. 0,05	0,02 – 0,15	Max. 0,1	Max. 0,3	1,7 – 2,8	Max. 0,1	Remaining	Max. 0,2																																																																																																																																																
Mechanical properties: EN 12164/12167 <table><tr><th rowspan="2">Material Condition</th><th rowspan="2">Diameter / Bar thickness mm</th><th rowspan="2">Width across flats mm</th><th rowspan="2">Rm MPa Min.</th><th rowspan="2">Rp_{0,2} MPa</th><th colspan="3">Elongation Min. %</th><th rowspan="2">Hardness HBW</th><th rowspan="2">Tolerance Class</th></tr><tr><th>A_{100 mm}</th><th>A_{11,3}</th><th>A</th></tr><tr><td colspan="10">≤ 80 mm Rods: EN 12164</td></tr><tr><td>R280</td><td>6 – 80</td><td>5 – 60</td><td>280</td><td>Max. 200</td><td>-</td><td>25</td><td>30</td><td>-</td><td rowspan="5">B</td></tr><tr><td>H070</td><td>6 – 80</td><td>5 – 60</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>70 – 110</td></tr><tr><td>R320</td><td>6 – 80</td><td>5 – 60</td><td>320</td><td>Min. 200</td><td>-</td><td>15</td><td>20</td><td>-</td></tr><tr><td>H090</td><td>6 – 80</td><td>5 – 60</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>90 – 135</td></tr><tr><td>R400</td><td>6 – 15</td><td>5 – 13</td><td>400</td><td>Min. 250</td><td>-</td><td>5</td><td>8</td><td>-</td></tr><tr><td colspan="10">> 80 mm Rods: EN 12165</td></tr><tr><td>M</td><td>80 < D</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>A</td></tr><tr><td colspan="10">Profiles & Bars: EN 12167</td></tr><tr><td>R280</td><td>3 – 20</td><td>-</td><td>280</td><td>Max. 200</td><td>10</td><td>20</td><td>30</td><td>-</td><td rowspan="5">B</td></tr><tr><td>H070</td><td>3 – 20</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>70 – 110</td></tr><tr><td>R320</td><td>3 – 20</td><td>-</td><td>320</td><td>Min. 200</td><td>4</td><td>10</td><td>20</td><td>-</td></tr><tr><td>H070</td><td>3 – 20</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>-</td><td>90 – 135</td></tr><tr><td>R400</td><td>3 – 10</td><td>-</td><td>400</td><td>Min. 250</td><td>2</td><td>2</td><td>8</td><td>-</td></tr></table>								Material Condition	Diameter / Bar thickness mm	Width across flats mm	Rm MPa Min.	Rp _{0,2} MPa	Elongation Min. %			Hardness HBW	Tolerance Class	A _{100 mm}	A _{11,3}	A	≤ 80 mm Rods: EN 12164										R280	6 – 80	5 – 60	280	Max. 200	-	25	30	-	B	H070	6 – 80	5 – 60	-	-	-	-	-	70 – 110	R320	6 – 80	5 – 60	320	Min. 200	-	15	20	-	H090	6 – 80	5 – 60	-	-	-	-	-	90 – 135	R400	6 – 15	5 – 13	400	Min. 250	-	5	8	-	> 80 mm Rods: EN 12165										M	80 < D	-	-	-	-	-	-	-	A	Profiles & Bars: EN 12167										R280	3 – 20	-	280	Max. 200	10	20	30	-	B	H070	3 – 20	-	-	-	-	-	-	70 – 110	R320	3 – 20	-	320	Min. 200	4	10	20	-	H070	3 – 20	-	-	-	-	-	-	90 – 135	R400	3 – 10	-	400	Min. 250	2	2	8	-
Material Condition	Diameter / Bar thickness mm	Width across flats mm	Rm MPa Min.	Rp _{0,2} MPa	Elongation Min. %								Hardness HBW	Tolerance Class																																																																																																																																										
					A _{100 mm}	A _{11,3}	A																																																																																																																																																	
≤ 80 mm Rods: EN 12164																																																																																																																																																								
R280	6 – 80	5 – 60	280	Max. 200	-	25	30	-	B																																																																																																																																															
H070	6 – 80	5 – 60	-	-	-	-	-	70 – 110																																																																																																																																																
R320	6 – 80	5 – 60	320	Min. 200	-	15	20	-																																																																																																																																																
H090	6 – 80	5 – 60	-	-	-	-	-	90 – 135																																																																																																																																																
R400	6 – 15	5 – 13	400	Min. 250	-	5	8	-																																																																																																																																																
> 80 mm Rods: EN 12165																																																																																																																																																								
M	80 < D	-	-	-	-	-	-	-	A																																																																																																																																															
Profiles & Bars: EN 12167																																																																																																																																																								
R280	3 – 20	-	280	Max. 200	10	20	30	-	B																																																																																																																																															
H070	3 – 20	-	-	-	-	-	-	70 – 110																																																																																																																																																
R320	3 – 20	-	320	Min. 200	4	10	20	-																																																																																																																																																
H070	3 – 20	-	-	-	-	-	-	90 – 135																																																																																																																																																
R400	3 – 10	-	400	Min. 250	2	2	8	-																																																																																																																																																
* Information values only;																																																																																																																																																								
Physical properties: <table><tr><th>Density (20 °C)</th><th>Solidification range</th><th>Electrical conductivity</th><th>Thermal conductivity (20 °C)</th><th>Thermal expansion (20 - 300 °C)</th><th>Annealing temperature</th><th>E – modulus (20 °C)</th></tr><tr><th>g/cm³</th><th>°C</th><th>%IACS</th><th>W/m K</th><th>μm m⁻¹ K⁻¹</th><th>°C</th><th>N / mm²</th></tr><tr><td>8,43</td><td>885</td><td>26</td><td>117</td><td>20,3</td><td>450 - 600</td><td>104000</td></tr></table>								Density (20 °C)	Solidification range	Electrical conductivity	Thermal conductivity (20 °C)	Thermal expansion (20 - 300 °C)	Annealing temperature	E – modulus (20 °C)	g/cm ³	°C	%IACS	W/m K	μm m ⁻¹ K ⁻¹	°C	N / mm ²	8,43	885	26	117	20,3	450 - 600	104000																																																																																																																												
Density (20 °C)	Solidification range	Electrical conductivity	Thermal conductivity (20 °C)	Thermal expansion (20 - 300 °C)	Annealing temperature	E – modulus (20 °C)																																																																																																																																																		
g/cm ³	°C	%IACS	W/m K	μm m ⁻¹ K ⁻¹	°C	N / mm ²																																																																																																																																																		
8,43	885	26	117	20,3	450 - 600	104000																																																																																																																																																		
Properties and information's (3 Excellent; 2 Good; 1 Poor/not recommendable) <table><tr><td> Machinability (Zerspanbarkeitsindex): 85* *(CuZn39Pb3 = 100) Forming Methods: Hot Formability: 2-3 Cold Formability: 1-2 Corrosion resistance: Atmosphere: 2 Waters and alkaline: 2 Acids, Ammonia, Seawater etc.: 1 </td><td> Joining Methods: Soldering: 3 Brazing: 2 Oxy-acetylene welding: 1 Gas-shielded arc welding: 1 TIG welding: 1 MIG welding: 1 Gluing/adhesion: 2 </td><td> Surface Treatment: Polishing: Mechanical: 2-3 Electrolytic/chemical: 1 Galvanizing: 3 Hot Dipping: 3 </td></tr></table>								Machinability (Zerspanbarkeitsindex): 85* *(CuZn39Pb3 = 100) Forming Methods: Hot Formability: 2-3 Cold Formability: 1-2 Corrosion resistance: Atmosphere: 2 Waters and alkaline: 2 Acids, Ammonia, Seawater etc.: 1	Joining Methods: Soldering: 3 Brazing: 2 Oxy-acetylene welding: 1 Gas-shielded arc welding: 1 TIG welding: 1 MIG welding: 1 Gluing/adhesion: 2	Surface Treatment: Polishing: Mechanical: 2-3 Electrolytic/chemical: 1 Galvanizing: 3 Hot Dipping: 3																																																																																																																																														
Machinability (Zerspanbarkeitsindex): 85* *(CuZn39Pb3 = 100) Forming Methods: Hot Formability: 2-3 Cold Formability: 1-2 Corrosion resistance: Atmosphere: 2 Waters and alkaline: 2 Acids, Ammonia, Seawater etc.: 1	Joining Methods: Soldering: 3 Brazing: 2 Oxy-acetylene welding: 1 Gas-shielded arc welding: 1 TIG welding: 1 MIG welding: 1 Gluing/adhesion: 2	Surface Treatment: Polishing: Mechanical: 2-3 Electrolytic/chemical: 1 Galvanizing: 3 Hot Dipping: 3																																																																																																																																																						

Tolerances for Bars of CW602N (Rods below)

Dimensions: EN 12167:2016*

Tolerances on width and thickness of bar

Nominal thickness t (mm)	Tolerance on width	Tolerance on thickness for range of thickness (mm)					
		3 < t ≤ 6	6 < t ≤ 10	10 < t ≤ 18	18 < t ≤ 30	30 < t ≤ 50	50 < t ≤ 60
Class B tolerance							
3 ≤ t ≤ 18	± 0,15	± 0,10	± 0,12	± 0,15	-	-	-
18 < t ≤ 30	± 0,22	± 0,10	± 0,12	± 0,15	± 0,22	-	-
30 < t ≤ 50	± 0,30	± 0,13	± 0,15	± 0,18	± 0,22	± 0,30	-
50 < t ≤ 80	± 0,37	± 0,16	± 0,18	± 0,22	± 0,30	± 0,37	-
80 < t ≤ 120	± 0,45	± 0,18	± 0,22	± 0,27	± 0,35	± 0,45	-

* Values are referred from Table 17 of EN 12167:2016

Dimensions: EN 12167:2016*

Tolerances on length of bar

Nominal width w (mm)	Preferred (available) lengths (mm)	Tolerance on length (mm)
$3 \leq w \leq 18$	3000, 4000	± 50
$18 < w \leq 30$	3000, 4000	± 100
$30 < w \leq 50$	2000, 3000, 4000	± 150
$50 < w \leq 80$	2000, 3000	± 200
$80 < w \leq 120$	1000, 2000	± 200

* Values are referred from Table 18 of EN 12167:2016

Dimensions: EN 12167:2016*

Tolerances on straightness of bar, for widths 10 mm and over

Tolerance class	Maximum deviation from straightness (mm)	
	Localized over any 400 mm length	Over whole length L of bar in metres ($L \geq 1m$)
A	2,4	$6,0 * L$
B	1,6	$4,0 * L$
C	0,8	$2,0 * L$

* Values are referred from Table 19 of EN 12167:2016

Dimensions: EN 12167:2016*

Maximum twist of bar

Nominal width w (mm)	Maximum permitted twist V in any 1000 mm length of bar (See Figure 2 in EN 12167:2016)		
	Class A	Class B	Class C
$3 \leq w \leq 18$	2,0	1,5	1,0
$18 < w \leq 30$	3,0	2,3	1,5
$30 < w \leq 50$	4,0	3,0	2,0
$50 < w \leq 80$	6,0	4,5	3,0
$80 < w \leq 120$	9,0	9,0	4,5

For bar of total length greater than 2000 mm, the permitted twist over the total length shall be twice the appropriate maximum given in the table for "in any 1000 mm".

* Values are referred from Table 20 of EN 12167:2016

Dimensions: EN 12167:2016*

Corner radii of bar

Nominal thickness t (mm)	Radii of corners	
	Sharp max.	Rounded range
$3 \leq t \leq 6$	0,3	0,3 – 0,5
$6 < t \leq 10$	0,4	0,4 – 0,8
$10 < t \leq 18$	0,5	0,5 – 1,2
$18 < t \leq 30$	0,6	0,6 – 1,8
$30 < t \leq 40$	0,7	0,7 – 2,8
$40 < t \leq 60$	0,8	0,8 – 4,0

NOTE: A bar having rounded corners of radius greater than those covered by this table is considered to be a profile

* Values are referred from Table 21 of EN 12167:2016

Tolerances for Rods of CW602N

Dimensions: EN 12163:2024*

Dimensional tolerances for rod

Nominal diameter or width across-flats	Tolerances	
	Class A	Class B
$1,6 \leq d/w \leq 3$	$\pm 0,10$	$\pm 0,05$
$3 < d/w \leq 6$	$\pm 0,15$	$\pm 0,08$
$6 < d/w \leq 10$	$\pm 0,20$	$\pm 0,11$
$10 < d/w \leq 18$	$\pm 0,25$	$\pm 0,14$
$18 < d/w \leq 30$	$\pm 0,30$	$\pm 0,17$
$30 < d/w \leq 50$	$\pm 0,60$	$\pm 0,20$
$50 < d/w \leq 80$	$\pm 0,70$	$\pm 0,37$

* Values are referred from Table 17 of EN 12163:2024

Dimensions: EN 12163:2024*

Tolerances on straightness of rod

Nominal diameter or width across-flats	Maximum deviation from straightness (See Figure 1 in EN 12163:2024)	
	h_2 depth of arch in any length l_2 of 400 mm	h_1 depth of arch in any length l_1 of 1000 mm
$10 \leq d/w \leq 50$	2,5	6,0

* Values are referred from Table 18 of EN 12163:2024

Dimensions: EN 12163:2024*

Corner radii for square and polygonal rod

Nominal width across-flats	Radii for sharp and rounded corners	
	Sharp max.	Rounded range
$1,6 \leq w \leq 3$	0,2	0,2 – 0,3
$3 < w \leq 6$	0,3	0,3 – 0,5
$6 < w \leq 10$	0,4	0,4 – 0,8
$10 < w \leq 18$	0,5	0,5 – 1,2
$18 < w \leq 30$	0,6	0,6 – 1,8
$30 < w \leq 50$	0,7	0,7 – 2,8
$50 < w \leq 80$	0,8	0,8 – 4,0

* Values are referred from Table 19 of EN 12163:2024

Dimensions: EN 12163:2024*

Maximum twist of square and polygonal rod

Nominal width across-flats w	Maximum permitted twist V in any 1 m length of rod
$10 \leq w \leq 18$	2,0
$18 < w \leq 30$	3,0
$30 < w \leq 60$	4,0

* Values are referred from Table 20 of EN 12163:2024

Dimensions: EN 12163:2024*

Sampling rate

Nominal width across-flats w (mm)	Mass of inspection lot for one test sample kg
$w \leq 25$	≤ 1000
$25 < w$	≤ 2000

* Values are referred from Table 21 of EN 12163:2024

Dimensions: EN 12165:2024*

Tolerances on diameter of round forging stock

Dimensions in millimetres

Nominal diameter	Tolerances
	Class A
$80 < D \leq 120$	± 2
$120 < D \leq 160$	$\pm 2,5$

* Values are referred from Table 10 of EN 12165:2024



Dimensions: EN 12165:2024*		
Tolerances on straightness of round forging stock		Dimensions in millimetres
Nominal diameter	Maximum deviation from straightness (See Figure 1 in EN 12164:2024)	
	<i>h2</i> <i>depth of arch in any length l2 of 400 mm</i>	<i>h1</i> <i>depth of arch in any length l1 of 1000 mm</i>
Straightness tolerances for rods over 60 mm diameter shall be agreed between the involved parties		