

Datasheet: EN CuZn42 / CW510L Classic Brass Profiles, Bars & Rods for general purposes Alumeco ApS 12-05-2025		Internal alloy name: CW510L Metal: Brass Chemical Symbol: CuZn42 EN: EN CuZn42 UNS: C28500 SIS: - GB: - JIS: - Also known as: - Alloy type: Classic Brass
Main usage: - Approved for contact with drinking water (4MS) - Faucets, hoses and other sanitary products	Important norms and literature: General Standards EN 12164:2024: Copper and copper alloys – Rod for free machining purposes Geometric Tolerance EN 12164:2024: Copper and copper alloys – Rod for free machining purposes EN 12165:2024: Copper and copper alloys – Wrought and unwrought forging stock	
Main properties: - Low lead content - Great formability properties - Excellent soldering properties		

Chemical composition in %: EN 12164:2024

Cu	Al	Fe	Ni	Pb	Sn	Zn	Others
57 – 59	Max. 0,05	Max. 0,3	Max. 0,3	Max. 0,2	Max. 0,3	Remaining	Max. 0,2

Mechanical properties: EN 12164 / EN 12165

Material Condition	Diameter / Bar thickness	Width across flats	Tensile Strength Rm	0,2% Proof Strength Rp _{0,2}	Elongation Min. %			Hardness HBW	Tolerance Class
	mm	mm	Min. MPa	MPa	A _{100mm}	A _{11,3}	A		
≤ 80 mm Rods: EN 12164									
R360	6 – 80	5 – 60	360	Max. 320	-	15	20	-	B
H090	6 – 80	5 – 60	-	-	-	-	-	90 – 125	
R430	2 – 40	2 – 35	430	Min. 220	6	8	10	-	
H110	2 – 40	2 – 35	-	-	-	-	-	110 – 160	
R500	2 – 14	2 – 10	500	Min. 350	-	3	5	-	
H135	2 – 14	2 – 10	-	-	-	-	-	Min. 135	
> 80 mm Rods: EN 12165									
M	80 < D	-	-	-	-	-	-	-	A

* Information values only;

Physical properties:

Density (20 °C) g/cm ³	Solidification range °C	Electrical conductivity %IACS	Thermal conductivity (20 °C) W/m K	Thermal expansion (20 - 300 °C) μm m ⁻¹ K ⁻¹	Annealing temperature °C	E – modulus (20 °C) N / mm ²
8,4	870 - 890	29	112	21,7	450 – 550	85000

Properties and information's (3 Excellent; 2 Good; 1 Poor/not recommendable)

Machinability (Zerspanbarkeitsindex): 60* *(CuZn39Pb3 = 100) Forming Methods: Hot Formability: 3 Cold Formability: 1-2 Corrosion resistance: Atmosphere: 2 Waters and alkaline: 2 Acids, Ammonia, Seawater etc.: 1	Joining Methods: Soldering: 3 Brazing: 3 Oxy-acetylene welding: 1 Gas-shielded arc welding: 2 TIG welding: 1-2 MIG welding: 1-2	Surface Treatment: <u>Polishing:</u> Mechanical: 3 Electrolytic/chemical: 2 <u>Galvanizing:</u> 3 <u>Hot Dipping:</u> 3
---	--	---

Tolerances for Rods of CW510L

Dimensions: EN 12164:2024*		Dimensions in millimetres
Tolerances on diameter of round rod		
Nominal diameter	Tolerances Class B	
$2 \leq D \leq 3$	0	- 0,025
$3 < D \leq 6$	0	- 0,030
$6 < D \leq 10$	0	- 0,036
$10 < D \leq 18$	0	- 0,043
$18 < D \leq 30$	0	- 0,052
$30 < D \leq 50$	-	
$50 < D \leq 80$	-	

* Values are referred from Table 16 of EN 12164:2024

Dimensions: EN 12164:2024*		Dimensions in millimetres
Tolerances on width across-flats of regular polygonal rod		
Nominal width across-flats	Tolerances	
$2 \leq W \leq 3$	0	- 0,06
$3 < W \leq 6$	0	- 0,08
$6 < W \leq 10$	0	- 0,09
$10 < W \leq 18$	0	- 0,11
$18 < W \leq 30$	0	- 0,13
$30 < W \leq 50$	0	- 0,16
$50 < W \leq 60$	0	- 0,19

* Values are referred from Table 17 of EN 12164:2024

Dimensions: EN 12164:2024*		Dimensions in millimetres
Tolerances on straightness of rod		
Nominal diameter	Maximum deviation from straightness (See Figure 1 in EN 12164:2024)	
	h_2 depth of arch in any length l_2 of 400 mm	h_1 depth of arch in any length l_1 of 1000 mm
$10 \leq D \leq 50$	0,4	1,0

* Values are referred from Table 18 of EN 12164:2024

Dimensions: EN 12164:2024*		Dimensions in millimetres
Corner radii for square and polygonal rod		
Nominal diameter or width across-flats	Preferred lengths	Tolerance on length
$2 \leq w \leq 30$	3000 or 4000	± 50
$30 < w \leq 50$	3000 or 4000	± 100
$50 < w \leq 80$	3000	± 100

* Values are referred from Table 19 of EN 12164:2024

Dimensions: EN 12164:2024*		Dimensions in millimetres
Corner radii for square, hexagonal and octagonal rod		
Nominal width across-flats	Radii for sharp and rounded corners	
	Sharp max.	Rounded range
$2 \leq w \leq 3$	0,2	0,2 – 0,3
$3 < w \leq 6$	0,3	0,3 – 0,5
$6 < w \leq 10$	0,4	0,4 – 0,8
$10 < w \leq 18$	0,5	0,5 – 1,2
$18 < w \leq 30$	0,6	0,6 – 1,8
$30 < w \leq 50$	0,7	0,7 – 2,8
$50 < w \leq 80$	0,8	0,8 – 4,0

* Values are referred from Table 20 of EN 12164:2024

Dimensions: EN 12164:2024* Maximum twist of square, hexagonal and octagonal rod		Dimensions in millimetres
Nominal width across-flats W	Maximum permitted twist V in any 1 m length of rod (mm)	
$10 \leq W \leq 18$	1,0	
$18 < W \leq 30$	2,0	
$30 < W \leq 60$	3,0	

* Values are referred from Table 21 of EN 12164:2024

Dimensions: EN 12164:2024* Sampling rate	
Nominal diameter or width across-flats w (mm)	Mass of inspection lot for one test sample kg
$D/W \leq 25$	≤ 1000
$25 < D/W$	≤ 2000

* Values are referred from Table 22 of EN 12164:2024

Dimensions: EN 12165:2024* Tolerances on diameter of round forging stock		Dimensions in millimetres
Nominal diameter	Tolerances Class A	
$80 < D \leq 120$	± 2	
$120 < D \leq 160$	$\pm 2,5$	

* Values are referred from Table 10 of EN 12165:2024

Dimensions: EN 12165:2024* Tolerances on straightness of round forging stock			Dimensions in millimetres
Nominal diameter	Maximum deviation from straightness (See Figure 1 in EN 12164:2024)		
	h_2 depth of arch in any length l_2 of 400 mm	h_1 depth of arch in any length l_1 of 1000 mm	
Straightness tolerances for rods over 60 mm diameter shall be agreed between the involved parties			